

MINOVA

FB400

HIGH STRENGTH, THIXOTROPIC ANCHORING GROUT



DESCRIPTION

FB400 is supplied as a ready-to-use, free-flowing, blended cementitious powder. It requires only the addition of water in a high shear mixer to produce a highly thixotropic grout.

APPLICATION AND USES

Designed for top-down cable bolt grouting, this solution is suitable for the effective grouting of long tendons in underground ground support applications.

ADVANTAGES

- > LoHigh early strength, reduces the likelihood of bed separation or slippage of strata
- > Thixotropic, can be used in badly broken ground
- > Non-shrink, unique expansion system compensates for shrinkage
- > High ultimate strength and low porosity ensures long term durability
- > Excellent pumpability
- > Chloride free

TECHNICAL PROPERTIES

Typical properties using potable water:

PUMPING LIFE @ 20°C (minutes)	SET TIME @ 20°C (minutes)
120	420

LITERS OF WATER PER BAG	8.0	7.0	6.0
AGE (days)	COMPRESSIVE STRENGTH (MPa)		
1 day	26	29	40
7 days	46	51	74
28 days	58	67	85
WET DENSITY (kg/m ³)	1867	1950	2030

APPLICATION METHOD

Preparation

Drill hole to desired depth, ensuring it is free and clear of loose matter for entire length. Position tendon in the hole. Ensure grout tube is at the top of the hole. Attach plate and tighten nut, then connect pumping hose.

Mixing

Water requirements are as follows:

- > Fill mixer with water as per Stage 1
- > Start mixer, then slowly add FB400 powder. If powder addition is too fast, large lumps will form, and final mix will be slow reaching uniformity.
- > Add remainder of water as per Stage 2 and mix until lump free.
- > Use a high shear mechanical mixer of approved design.

	LITRES/20KG BAG	LITRES/15KG BAG
Stage 1	6.0L	4.5L
Stage 2	1.0L	0.75L
Total	7.0L	5.25L
Maximum	8.0L	6.0L

Placing

- > Continuous flow of grout is essential, therefore prepare enough grout for the job prior to placement. Do not try to mix and place grout at the same time.
- > Connect the pump to the grout filling tube
- > Pump the grout into the bolt hole until the grout emerges from the bottom of the hole.

Cleaning

FB400 should be removed from tools and equipment immediately after use with clean water.

PACKAGING AND TRANSPORTATION

FB400 is supplied in 20kg & 15kg bags. All bags are packed on stretch-wrapped wooden pallets, 60 bags per pallet.

DISCLAIMER

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

SAFETY INSTRUCTIONS AND LIMITATIONS

At the recommended consistency, the approximate grout yield is as follows:

YIELD / 20KG BAG	YIELD / 15KG BAG
15L	11.25L

STORAGE CONDITIONS AND SHELF LIFE

FB400 has a shelf life of 12 months. FB400 should be stored in original packing under dry warehouse conditions. High temperature and high humidity may reduce the shelf life.

TECHNICAL SUPPORT

We provide technical advisory service by a team of specialists in the field. The service includes on-site assistance and advice on evaluation trials and laboratory work.

MANUFACTURER

Minova Australia Inc

An ISO 9001:2015

Quality Management Certified Company

Certificate No. FM 689118



CUSTOMER SERVICE

(1800 Minova) 1800 646 682

Email: sales_au@minovaglobal.com

Website: www.minovaglobal.com