

MINOVA

LOKSET™

RESIN CAPSULE

TOOSPEEDIE™



DESCRIPTION

Lokset™ TOOSPEEDIE™ eliminates the need to use multiple resin Capsules to achieve pre-tensioning of fully encapsulated resin grouted rock bolts.

The Capsules are available in multiple set time ratios allowing for various combinations of set times.

Lokset TOOSPEEDIE Resin Capsules consist of fast and slow speed polyester resin mastic in one sausage-shaped Capsule. One Capsule compartmentalizes a resin mastic, and the other compartment a catalyst hardener.

Lokset TOOSPEEDIE products are used in conjunction with steel (rebar) and cable bolts. Insertion and rotation of the bolt ruptures the Capsule, shreds the film, and mixes the two components, thus causing a chemical reaction which transforms the resin mastic to a rock-solid anchor.

Lokset TOOSPEEDIE Resin Capsules are available for A, and B Series applications as well as High, Medium, Low and Very Low Insertion Force viscosities.

APPLICATIONS AND USES

Lokset TOOSPEEDIE is used for permanent rock reinforcement in mines, tunnels and foundations.

ADVANTAGES

- > Proven – decades of use in the United States
- > Rapid – enables fast installation with application of load in minutes
- > Efficient – allows roof bolt to be tensioned immediately after installation

APPLICATION METHOD

Contact your local Minova representative if the Lokset TOOSPEEDIE Resin Capsules is to be used in other applications.

1. Before use, read the installation and safety information provided to include the product Safety Data Sheet (SDS).
2. To obtain a consistent set time, make sure the Lokset TOOSPEEDIE Resin Capsules and bolt are at a minimum 50°F temperature before use.
3. Drill the borehole to the correct diameter at a depth equal to the length of the bolt plus 1-inch. Mark the drill steel to use as a guide.
4. Insert the appropriate Capsule and push the bolt into the hole. Slow rotation of the bolt as it passes through the Capsule is suggested but not required. Ensure each capsule is completely punctured.
5. Just below the roof, stop and spin the bolt a minimum of 35 revolutions to mix the Capsule. This should take 3 to 8 seconds.
6. Stop rotation and push the bolt upward with full thrust until the resin sets.

SAFETY INSTRUCTIONS AND LIMITATIONS

Do not over-spin the bolt. If bolt rotation continues through the gel time, damage to the setting resin may occur.

Never re-rotate the bolt. Bolt rotation after the final spin may damage the partially set resin.

Observe the usual precautionary measures for handling chemicals, see Lokset™ TOOSPEEDIE™ Resin Capsule SDS. Insert the appropriate Capsule and push the bolt into the hole. Slow rotation of the bolt as it passes through the Capsule is suggested but not required. Ensure each capsule is completely punctured.

PACKAGING AND TRANSPORTATION

Product packaging is dependent upon capsule length. Please contact a Minova Customer Service Representative for packaging information.

STORAGE AND SHELF LIFE

Lokset TOOSPEEDIE Resin Capsules can be stored for 12 months in a cool dry, ventilated place. Store away from direct sunlight or other heat sources which can reduce products usability and shelf life.

DISPOSAL

If this product as supplied becomes a waste, it does not meet the criteria of a hazardous waste as defined under the Resource Conservation and Recovery Act (RCRA) 40 CFR 261. Dispose of material in accordance with all applicable federal, state/provincial and local laws and regulations. Regulations may vary in different locations. Waste characterizations and compliance with applicable laws are the responsibility solely of the waste generator.

DISCLAIMER

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

MANUFACTURER

Minova Canada Inc

An ISO 9001:2015

Quality Management Certified Company
Certificate No. FM 686583

Original Registration Date: 1995-02-15

Latest Revision Date: 2025-02-06



CUSTOMER SERVICE

Minova Canada Inc

29 Linden Street

Hamilton, Ontario

L8L 8E1

Email: sales.canada@minovaglobal.com